



High Power Output

SMBB technology reduces the distance between busbars and finger grid lines, improving reliability and increasing output



ZERO LID (Light Induced Degradation)

N-type solar cell has no LID naturally which can increase power generation



Higher Reliability

Adpoted Jolywood lastest J-TOPCon2.0 technology, No polysilicon wrap around, Full electrical isolation, Zero leakage current; Much Safer for roof



Jolywood Delivers Reliable Performance Over Time

- Leader of N-type bifacial manufacturer
- Full-automatic facility and industry-leading technology
- · Best-in-class durability and reliability
- BNEF Tier One



Better Weak Illumination Response

Higher power output even under low-light environments like on cloudy or foggy days



Better Temperature Coefficient

Higher power generation under working conditions, thanks to passivating contact cell technology



Lighter Module Weight

Reduces weight by more than 20% compared to bifacial double glass module

Linear Performance Warranty



[&]quot;Subject to the terms and conditions contained in the applicable Jolywood Solar Limited Warranty Statement. Also this 15 -year limited product warranty is available only for products installed and operating on residential rooftops in certain reg



Electrical Properties STC*						
Testing Condition	Front Side					
Peak Power (Pmax) (W)	420	425	430	435	440	445
MPP Voltage (Vmp) (V)	31.9	32.1	32.3	32.5	32.7	32.9
MPP Current (Imp) (A)	13.17	13.24	13.32	13.39	13.46	13.53
Open Circuit Voltage (Voc) (V)	37.9	38.1	38.3	38.4	38.6	38.8
Short Circuit Current (Isc) (A)	13.98	14.05	14.12	14.18	14.25	14.32
Module Efficiency (%)	21.51	21.76	22.02	22.27	22.53	22.79

*STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5

The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

Electrical Properties	NOCT*					
Testing Condition	Front Side					
Peak Power (Pmax) (W)	318	322	326	330	334	338
MPP Voltage (Vmp) (V)	30.0	30.2	30.3	30.5	30.7	30.9
MPP Current (Imp) (A)	10.62	10.67	10.74	10.82	10.88	10.94
Open Circuit Voltage (Voc) (V)	36.2	36.4	36.6	36.8	37.0	37.2
Short Circuit Current (Isc) (A)	11.27	11.33	11.38	11.44	11.49	11.54

*NOCT: Irradiance 800 W/m², Ambient Temperature 20°C, Wind Speed 1 m/s

Temperature Coefficient	
Temperature Coefficient of Pmax*	-0.300%/°C
Temperature Coefficient of Voc	-0.250%/°C
Temperature Coefficient of Isc	+0.045%/°C
Nominal Operating Cell Temperature (NOCT)	42±2°C


*Temperature Coefficient of Pmax±0.03%/°C

r reemanneat i roperties	
Cell Size	182.00mm*91.00mm
Number of Cells	108pcs(12*9)
Module Dimension	1722mm*1134mm*30mm
Weight	21.5kg
Front Glass*	3.2mm
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm², +300mm/-180mm (Cable length can be customized)
Country of Origin	China
Fire Rating	С
Connector Model	QC Solar QC4.10-cd / Staubli EVO2
*Fully strengthened glass	


Partner Section

NOIE:				
:				

Engineering Drawing (unit: mm



Characteristic Curves | HT108N-420



Packaging Configuration							
Packing Type	20'GP	40'GP	40'HQ				
Piece/Pallet		36					
Pallet/Container	6	13	26				
Piece/Container	216	468	936				

*The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement, Jolywood (Taizhou) Solar Technology Co., Ltd. reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datasheet which shall be duly incorporated into the binding contract made by the parties governing all transactions related to the purchase and sale of the products described herein.



