



(X) JOLYWOOD

IEC61215(2016), IEC61730(2016) | ISO9001:2015: Quality Management System | ISO14001:2015: Environment Management System ISO45001:2018: Occupational health and safety management systems | IEC62941: 2019: Quality system for PV module manufacturing



# **High Power Output**

SMBB technology reduces the distance between busbars and finger grid lines, improving reliability and increasing output



### **ZERO LID (Light Induced Degradation)**

N-type solar cell has no LID naturally which can increase power generation



# **Higher Reliability**

Adpoted Jolywood lastest J-TOPCon2.0 technology, No polysilicon wrap around, Full electrical isolation, Zero leakage current; Much Safer for roof



### Jolywood Delivers Reliable Performance Over Time

- Leader of N-type bifacial manufacturer
- Full-automatic facility and industry-leading technology
- · Best-in-class durability and reliability
- BNEF Tier One



## **Better Weak Illumination Response**

Higher power output even under low-light environments like on cloudy or foggy days



### **Better Temperature Coefficient**


Higher power generation under working conditions, thanks to passivating contact cell technology



## **Outstanding visual appearance**

Designed with aesthetics in mind, thinner wires that appear all black at a distance

### **Linear Performance Warranty**











Electrical Properties	STC*					
Testing Condition	Front Side					
Peak Power (Pmax) (W)	415	420	425	430	435	440
MPP Voltage (Vmp) (V)	31.7	31.9	32.1	32.3	32.5	32.7
MPP Current (Imp) (A)	13.10	13.17	13.24	13.32	13.39	13.46
Open Circuit Voltage (Voc) (V)	37.7	37.9	38.1	38.3	38.4	38.6
Short Circuit Current (Isc) (A)	13.91	13.98	14.05	14.12	14.18	14.25
Module Efficiency (%)	21.25	21.51	21.76	22.02	22.27	22.53

\*STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5
The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

Electrical Properties	NOCT*					
Testing Condition	Front Side					
Peak Power (Pmax) (W)	315	318	322	326	330	334
MPP Voltage (Vmp) (V)	29.8	30.0	30.2	30.3	30.5	30.7
MPP Current (Imp) (A)	10.56	10.62	10.67	10.74	10.82	10.88
Open Circuit Voltage (Voc) (V)	36.0	36.2	36.4	36.6	36.8	37.0
Short Circuit Current (Isc) (A)	11.22	11.27	11.33	11.38	11.44	11.49

### Operating Temperature (°C) -40°C~+85°C Maximum System Voltage (V) 1500V DC (IEC) Maximum Series Fuse Rating (A) 30 Power Tolerance 0~+5W

Temperature Coefficient		
Temperature Coefficient of Pmax*	-0.300%/℃	
Temperature Coefficient of Voc	-0.250%/℃	
Temperature Coefficient of Isc	+0.045%/°C	
Nominal Operating Cell Temperature (NOCT)	42±2℃	

<sup>\*</sup>Temperature Coefficient of Pmax±0.03%/°C


Mechanical Properties	
Cell Size	182.00mm*91.00mm
Number of Cells	108pcs(12*9)
Module Dimension	1722mm*1134mm*30mm
Weight	21.5kg
Front Glass*	3.2mm
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm², +300mm/-180mm (Cable length can be customized )


\*Fully strengthened glass

# NOTE:

JOLYWOOD (TAIZHOU) SOLAR

www.jolywood.cn





Packaging Configuration					
Packing Type	20'GP	40'GP	40'HQ		
Piece/Pallet		36			
Pallet/Container	6	13	26		
Piece/Container	216	468	936		



Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone, Taizhou, Jiangsu Province, China, 225500

TECHNOLOGY CO.,LTD. TEL: +86 523 80612799 Email: mkt@jolywood.cn

